PA 4535 CF Filament

JABIL

Recommended Print Settings



Print Temperature

The optimal printing range is 250 - 270°C



Bed Temperature

A bed temperature of 60° C will provide the best adhesion during printing.



Printing Speed

Base printing speed of 60 mm/s Infill speed of 60 mm/s Wall speed of 40 mm/s Initial layer speed of 20 mm/s



Cooling

Fan Speed: 10%



Bed Adhesion

PVA Glue Stick



Other Tips

- Filament is very stiff and can create feeding issues, these can be mitigated if a small amount of moisture is absorbed from the atmosphere without sacrificing print quality.
- Hardened steel or ruby tipped nozzles are required.

PA 4535 CF Filament

JABIL

PA 4535 CF is among the strongest PA co-polymer carbon fiber filaments available on the market, delivering increased strength and stiffness. PA 4535 CF has the highest carbon fiber loading available in the industry, providing 40% improvement in tensile strength, impact strength, Z strength and elongation at break, with the added benefit of being ESD safe.

Applications

Great for parts requiring increased stiffness and strength

Examples include:

- · Aluminum replacement parts
- Housings requiring tight printing dimensional tolerances
- Jigs, fixtures and tooling
- Clips
- Brackets
- Retainers
- Covers
- Housings

Advantages

- 40% increase in stiffness and tensile strength over lower carbon fiber-loaded products
- · No reduction in impact strength
- Improved Z layer properties
- Electrostatic dissipative (ESD)
- · Almost no shrinkage or curl

Prints on open platforms including Ultimaker S5, Raise3D, Method X and Taz® Pro Platforms

Diameters

1.75mm and 2.85mm

