

CTPU-35

PRODUCT DESCRIPTION

Jabil's ether-based TPU pellet boasts a high level of electrical conductivity, making it ideal for use in industries such as electronics, automotive, and aerospace. With excellent mechanical properties and a wide temperature range, this pellet can withstand harsh environments and extreme conditions without compromising its conductivity.

This pellet is easy to process, whether you are using an extrusion or injection molding machine. Its consistent and uniform size ensures reliable and consistent output every time. Its unique formulation also ensures that it is compatible with a wide range of processing conditions, making it a versatile choice for your manufacturing needs.

PROPERTIES

MECHANICAL PROPERTIES¹

	Test Condition	Typical Values	Method
Tensile Modulus (MPa)	IM Coupons	100	ASTM D638, Type I
Tensile Stress @ 10% Elongation (MPa)	IM Coupons	6.5	ASTM D638, Type I
Tensile Stress @ 100% Elongation (MPa)	IM Coupons	14.4	ASTM D638, Type I
Tensile Elongation at Break (%)	IM Coupons	202	ASTM D638, Type I
Ultimate Tensile Strength (MPa)	IM Coupons	15.2	ASTM D638, Type I
Tear Strength (N/mm)	IM Coupons	66	ASTM D638, Type I

¹Testing conducted on coupons molded at 210°C. Typical values are for reference only.

THERMAL PROPERTIES

	Test Condition	Typical Values	Method
Melt Onset Temperature (°C)	20°C/min ramp	167	DSC

ELECTRICAL PROPERTIES

	Test Condition	Typical Values	Method
Surface Resistivity (ohms/square)	Ambient	1E+03	ASTM D257

OTHER PHYSICAL PROPERTIES

	Test Condition	Typical Values	Method
Density (g/cm ³)	Ambient	1.28	ASTM D792
Shore A Hardness	Ambient	97	ASTM D2240
Shore D Hardness	Ambient	63	ASTM D2240

*Burn properties are highly dependent upon printer settings and part geometry. Suitability for an application is the responsibility of the user.

Disclaimer: The information in this technical data sheet, including material properties, are obtained from testing representative samples under carefully controlled conditions and are provided for reference only. Material properties may be impacted by storage, handling, processing equipment/parameters, and product design, among other factors. The information is not a substitute for user testing to determine fitness for any specific use and the user is responsible for ensuring safe and lawful use of the product.

No express or implied warranties are provided and the implied warranties of merchantability or fitness for a particular purpose are expressly disclaimed. No representations are made, and no liability is assumed arising from or relating to the product.

For additional information, visit
jabil.com

About Jabil

Jabil (NYSE: JBL) is a manufacturing solutions provider with over 250,000 employees across 100 locations in 30 countries. The world's leading brands rely on Jabil's unmatched breadth and depth of end-market experience, technical and design capabilities, manufacturing knowhow, supply chain insights and global product management expertise. Driven by a common purpose, Jabil and its people are committed to making a positive impact on their local community and the environment.