

TPE-SEBS 1300 95A Filament

Recommended Print Settings

JABIL



Print Temperature

The optimal printing range is 230° – 270°C



Cooling

For best results, do not use a cooling fan while printing with TPE-SEBS.



Bed Temperature

A bed temperature of 50°C to 70°C will provide the best adhesion during printing.



Bed Adhesion

Use a brim while printing on clean glass or a PEI sheet. No glue or extra adhesion method is necessary.



Printing Speed

Base printing speed of 25 mm/s
Infill speed of 15-25 mm/s
Wall speed of 15-25 mm/s
Initial layer speed of 15-25 mm/s



Other Tips

- If the material starts to short feed or bind up in the extruder, turn down the feeder wheel tension. It is recommended to start with as little tension as possible.
- Using a PTFE or fluoropolymer-lined tubing will help with printing. Using this type of tube will allow the print temperature to be lower.

If using Ultimaker Cura, enable the Jabil TPE-SEBS 1300 95A material profile available in the Marketplace or manually type in the settings from the information above.

Disclaimer: Due to the large variety of printers and part geometries, the given process parameters are a guideline.

© 2020 Jabil, Inc.

TPE-SEBS 1300 95A Filament

JABIL

TPE-SEBS 95A is a soft material great for prototyping where rubber-like or elastomeric properties and durability are required. TPE-SEBS 1300 95A is slightly firmer than TPE-SEBS 1300 85A for application requirements that call for flexibility but also need more rigidity to achieve the optimal finished part performance.

Applications

- Automotive, aerospace, general manufacturing
- Parts that require toughness and resilience as well as some flexibility and fatigue resistance along with elastomeric properties that can bend, flex and stretch
- Complex geometries

Examples include:

- Automotive interior trim components
- Packaging closures
- Covers and housings
- Grips
- No slip feet for electronic and mechanical components
- Gap seals

Advantages

- High print success rates
- Very low warpage and curl
- No need for heated print bed or drying requirements
- Shore 95A elastomer
- High flexibility, bend and stretch
- Non-hygroscopic, does not absorb moisture
- Durable with repetitive motions
- Less visible layer lines, less warp

Diameters

1.75mm and 2.85mm



jabil.com/filaments

Questions? Contact us:
JabilAdditive@jabil.com



Learn More About
TPE-SEBS 1300 95A

For the latest print profiles, search for Jabil
Engineered Materials in the Cura Marketplace.